

UNS No.	ASTM	EN	JIS	FOCT	Chemical Composition (%)									
					C	Mn	P	S	Si	Cr	Ni	Mo	Ti	N
S30400	TP304	1.4301	SUS304	08X18H10	≤0.08	≤2.00	≤0.045	≤0.030	≤1.00	18.0-20.0	8.0-11.0	-	-	-
S30403	TP304L	1.4307	SUS304L	03X18H11	≤0.035	≤2.00	≤0.045	≤0.030	≤1.00	18.0-20.0	8.0-13.0	-	-	-
S30409	TP304H	1.4948	SUS304H	-	0.04-0.10	≤2.00	≤0.045	≤0.030	≤1.00	18.0-20.0	8.0-11.0	-	-	-
S31600	TP316	1.4401	SUS316	-	≤0.08	≤2.00	≤0.045	≤0.030	≤1.00	16.0-18.0	11.0-14.0	2.00-3.00	-	-
S31603	TP316L	1.4404	SUS316L	03X17H14M2	≤0.035	≤2.00	≤0.045	≤0.030	≤1.00	16.0-18.0	10.0-14.0	2.00-3.00	-	-
S31635	TP316Ti	1.4571	SUS316Ti	08X17H13M2T	≤0.08	≤2.00	≤0.045	≤0.030	≤0.75	16.0-18.0	10.0-14.0	2.00-3.00	5x(C+N)- 0.70	≤0.10
S32100	TP321	1.4541	SUS321	08X18H10T	≤0.08	≤2.00	≤0.045	≤0.030	≤1.00	17.0-19.0	9.0-12.0	-	5xC-0.70	≤0.10
S32109	TP321H	1.4940	SUS321H	-	0.04-0.10	≤2.00	≤0.045	≤0.030	≤1.00	17.0-19.0	9.0-12.0	-	4xC-0.60	-

\*Other Special steel grades upon request.